

iD INSPIRATION 55-70

iD INSPIRATION 55-70^{PLUS}

TECHNICAL DATA

Certification & classification	Standards	iD Inspiration 55 / iD Inspiration 55 ^{PLUS}	iD Inspiration 70 / iD Inspiration 70 ^{PLUS}
Type of floor covering	EN ISO 10582	Heterogeneous Compact Resilient Floorcovering	Heterogeneous Compact Resilient Floorcovering
Classification	EN ISO 10874	Domestic: 23 Commercial: 33 Industrial: 42	Domestic: 23 Commercial: 34 Industrial: 43
Technical characteristics			
Total thickness	EN ISO 24346	2,5 mm	2,5 mm
Wear layer thickness	EN ISO 24340	0,55 mm	0,7 mm
Total weight	EN ISO 23997	4000 g/m ²	4000 g/m ²
Wear layer binder content	EN ISO 10582	Type I	Type I
Dimensions	EN ISO 24342 Planks	16,66 x 100 cm, 22 planks/box = 3,67 m ² 12,5 x 122 cm, 24 planks/box = 3,66 m ² 20 x 122 cm, 15 planks/box = 3,66 m ² 25 x 122 cm, 12 planks/box = 3,66 m ² 25 x 150 cm, 10 planks/box = 3,75 m ² 50 x 100 cm, 7 planks/box = 3,50 m ²	
	Tiles	25 x 50 cm, 30 tiles/box = 3,75 m ² 50 x 50 cm, 15 tiles/box = 3,75 m ² 50 x 100 cm, 7 tiles/box = 3,50 m ² 100 x 100 cm, 3 tiles/box = 3 m ²	
Surface treatment (PUR)		TopCleanXP™	TopCleanXP™
Beveled edges		Yes	Yes
Technical performances			
Dimensional stability	EN ISO 23999	≤ 0,10 %	≤ 0,10 %
Curl resultant to heat	EN ISO 23999	≤ 2 mm	≤ 2 mm
Reaction to fire	EN 13501-1	B _{fl} -s1 glued on wood panel and concrete	B _{fl} -s1 glued on wood panel and concrete
Residual indentation	EN ISO 24343-1	≤ 0,05 mm	≤ 0,05 mm
Furniture leg	EN 424	No damage	No damage
Castor chair	ISO 4918 - EN 425	No damage	No damage
Impact sound reduction	EN ISO 717-2	ΔL _w = 2 dB	ΔL _w = 2 dB
Reduction of in-room impact noise	EN ISO 31-074	Class C (L _{n,e,w} < 85 dB)	Class C (L _{n,e,w} < 85 dB)
Thermal resistance	EN ISO 10456	0,02 m ² K/W	0,02 m ² K/W
Light fastness	EN ISO 105-B02 (method 3a)	≥ 6	≥ 6
Chemical resistance	EN ISO 26987	Not affected (0)	Not affected (0)
Slip resistance	DIN 51130 EN 13893	R9 / R10 depending on embossing μ ≥ 0,30	R9 / R10 depending on embossing μ ≥ 0,30
Electrical properties	EN 1815 EN 1081	<2 kV on concrete > 10 ⁹ Ohm	<2 kV on concrete > 10 ⁹ Ohm
Peeling resistance	EN ISO 24345	≥ 50N / 50mm	≥ 50N / 50mm
Underfloor heating		Suitable - max. 27 °C	Suitable - max. 27 °C

The above information is subject to modification for the benefit of further improvement. (01/17).

Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for these instructions.

CUSTOMS TARIFF : 4820 5000 00

